

Polymer Systems Technology Limited

UK & Ireland Distributor



© 2011 - Polymer Systems Technology Limited TM
Unit 2. Network 4. Cressex Business Park,
Lincoln Road, High Wycombe, Bucks. HP12 3RF
Phone +44 (0) 1494 446610
Fax: +44 (0) 1494 528611
Web: <http://www.siliconepolymers.co.uk>
Email: sales@silicone-polymers.co.uk



MED-6385

Silicone Elastomer

Product Profile

Description

- Pourable, two-component silicone
- 100:0.5 Mix Ratio (Base:Curing Agent)

Applications

- Useful in various medical prostheses
- Use as a mold making material and as a splint for holding tissue in place

Typical Properties	Result	Metric Conv.	ASTM	NT-TM
Uncured:				
Appearance	Gray to Tan	-	D2090	002
Viscosity	45,000 cP	45,000 mPas	D1084, D2196	001
Work Time	7 minutes	-	-	008
Cured: 24 hours @ ambient temperature and humidity				
Specific Gravity	1.13	-	D792	003
Durometer, Type A	45	-	D2240	006
Tensile Strength	500 psi	3.4 MPa	D412	007
Elongation	175%	-	D412	007

Instructions for Use

Mixing

Add 0.5% by weight catalyst to the base material and mix thoroughly for two minutes. If an air-free mixture is desired, then vacuum de-air the mixture to minimize trapped air bubbles.

Vacuum Deaeration

Remove air entrapped during mixing by common vacuum deaeration procedure, observing all applicable safety precautions. Slowly apply vacuum, up to 28 inches of Hg, to a container rated for use at least four times the volume of material being de-aired. Hold vacuum until bulk deaeration is complete.

Packaging

1 Pint Kit (458 g)
 1 Gallon Kit (3.66 kg)
 5 Gallon Kit (18.3 kg)

Warranty

6 Months

FDA Master Access File

A Master Access File for MED-6385 will be filed with the U.S. Food and Drug Administration. Customers interested in authorization to reference the Master Access File must contact NuSil Technology.

Warnings About Product Safety

NuSil Technology believes the information and the data contained herein are accurate and reliable. However, the user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please contact NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and contact NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, obtain available product safety information and take the necessary steps to ensure safety of use.

Specifications

Do not use the typical properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

Patent Warning

NuSil Technology disclaims any expressed or implied warranty against the infringement of any patent. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any United States' or other country's patents covering the product itself, its use in combination with other products or its use in the operation of any process.

Warranty Information

NuSil Technology's warranty period is 6 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims any other expressed or implied warranty, including warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.